

HI835MU

Description

Impact resistance grade
High UV protection
Good for exterior application
High light transmission
Good mechanical strength, surface hardness, weather resistance

Application

Home appliance cover housing & front door, UV-Blocking sheet/Film
Road Traffic sign, Multi-wall sheet, Corrugated sheet

Table

항목	조건	단위	검사방법	값
광학적 성질				
굴절률	nd	-	ISO 489	1.49
광투과율	3mm	%	ISO 13468-1	91
Haze	3mm	%	ISO 14782	<1.5
열적 성질				
유동성	230°C/3.8kg	g/10min	ISO 1133	3.3
VICAT 연화점	B/50	°C	ISO 306	93
열변형온도_annealed	1.8MPa	°C	ISO 75	90
선팅창계수	-	1/°C	ASTM D696	7X10 ⁻⁵
기계적 성질				
Charpy 충격강도	notched	kJ/m ²	ISO 179	3.2
Rockwell 경도	M scale	-	ISO 2039-2	70
인장강도	5mm/min	MPa	ISO 527	43
인장신율	5mm/min	%	ISO 527	35
인장탄성률	1mm/min	GPa	ISO 527	2.0
굴곡강도	2mm/min	MPa	ISO 178	81
굴곡탄성률	2mm/min	GPa	ISO 178	2.0
일반 성질				
비중	-	g/cm ³	ISO 1183	1.17
성형 수축률	-	%	ASTM D955	0.4-0.8
수분흡수율	24hr	%	ASTM D570	0.4
Flammability UL94	1.5mm	Class	IEC 60695-11-10	HB
추천 가공 조건				
예비 건조 온도	제습 건조	°C	-	70-80
예비 건조 시간	제습 건조	hr	-	4-6
용융 온도	-	°C	-	210-240
금형 온도	-	°C	-	50-70

REMARKS : The listed values should be used for reference purpose only.