

PMMA
Paintless Black Grade

IH830XT-9678

Description

Appropriate for injection molding
High-heat resistant grade
Good surface hardness & abrasion resistance, High gloss,
Excellent weatherability
Environment-friendly, Cost-reduction

Application

Exterior molding garnish, Door frame garnish (B, C pillar), Tail lamp edge black

Table

PROPERTY	CONDITION	UNIT	METHOD	VALUE
THERMAL PROPERTIES				
Melt Flow Index	230°C/3.8kg	g/10mn	ISO 1133	2.4
VICAT Softening Point	B/50	°C	ISO 306	114
Heat Deflection Temperature	1.8MPa	°C	ISO 75	104
Coefficient of Linear Expansion	-	1/°C	ASTM D696	6x10 ⁻⁵
MECHANICAL PROPERTIES				
Charpy Impact Strength	notched	kJ/m ²	ISO 179	1.5
Rockwell Hardness	M scale	-	ISO 2093-2	99
Tensile Strength at Break	5mm/min	MPa	ISO 527	68
Tensile Strain at Break	5mm/min	%	ISO 527	4
Tensile Modulus	1mm/min	GPa	ISO 527	3.1
Flexural Strength	2mm/min	MPa	ISO 178	115
Flexural Modulus	2mm/min	GPa	ISO 178	3.2
GENERAL PROPERTIES				
Density	-	g/cm ³	ISO 1183	1.19
Mold Shrinkage	-	%	ASTM D955	0.2-0.6
Water Absorption	24hr	%	ASTM D570	0.3
Flammability (UL94)	1.5mm	Class	IEC 60695-11-10	HB
RECOMMENDED PROCESSING CONDITIONS				
Predrying Temperature	-	°C	-	90-100
Predrying Time in Desiccant-Type Drier	-	hr	-	4-6
Melt Temperature	-	°C	-	230-260
Mold Temperature	-	°C	-	60-90

REMARKS : The listed values should be used for reference purpose only.