

PMMA  
Paintless Black Grade

# HI835MS-9678

## Description

Appropriate for injection molding  
Slightly impact grade with medium heat resistance  
High gloss, High mechanical strength, Excellent weatherability  
Recycleable, Environment-friendly, Cost-reduction  
Mold flow simulation data is available

## Application

Exterior molding garnish, Door frame garnish (B,C,D pillar), Car front grill & rear deco  
Side mirror base plate cover

## Table

항목	조건	단위	검사방법	값
<b>열적 성질</b>				
유동성	230°C/3.8kg	g/10min	ISO 1133	1.8
유동성	220°C/10kg	g/10min	ISO 1133	3.4
VICAT 연화점	B/50	°C	ISO 306	102
열변형온도_annealed	1.8MPa	°C	ISO 75	98
선팽창계수	-	1/°C	ASTM D696	7X10 <sup>-5</sup>
<b>기계적 성질</b>				
Charpy 충격강도	notched	kJ/m2	ISO 179	2.6
Rockwell 경도	M scale (*R)	-	ISO 2039-2	78 / 120(*R)
인장강도	5mm/min	MPa	ISO 527	67
인장신율	5mm/min	%	ISO 527	30
인장탄성률	1mm/min	GPa	ISO 527	2.5
굴곡강도	2mm/min	MPa	ISO 178	85
굴곡탄성률	2mm/min	GPa	ISO 178	2.4
<b>일반 성질</b>				
비중	-	g/cm <sup>3</sup>	ISO 1183	1.18
성형 수축률	-	%	ASTM D955	0.4-0.8
수분흡수율	24hr	%	ASTM D570	0.4
Flammability UL94	1.5mm	Class	IEC 60695-11-10	HB
<b>추천 가공 조건</b>				
예비 건조 온도	제습 건조	°C	-	70-80
예비 건조 시간	제습 건조	hr	-	4-6
용융 온도	-	°C	-	210-240
금형 온도	-	°C	-	60-80

REMARKS : The listed values should be used for reference purpose only.